



TECHNICAL BULLETIN
TECHNICAL BULLETIN

PRODUCT INFORMATION

ULTIMEG 2000-375

ANTI TRACKING

AIR DRYING ALKYD

GOLDEN

READY FOR USE

ULTIMEG 2000-375 ANTI-TRACKING ENAMELS AND VARNISHES

GENERAL DESCRIPTION

The Ultimeg 2000-375 anti-tracking varnish provides a tough, impervious, insulating seal in difficult environments. The system dries rapidly in thin film to give very effective sealing off of electrical leakage paths together with excellent noise reduction characteristics. The cured product conforms to BS 5629 type 1.1 (IEC 85), has excellent resistance to transformer oils and moisture, and is suitable for use in Class B and F insulating systems. A low hazard fungicide is included in the varnished enamels which gives a 0 rating (no growth) fungal resistance when tested to BS 3900 PTG6. This makes the system particularly suited for tropicalisation and for use on equipment working in warm humid climates.

APPLICATION

Suitable for noise reduction in small transformers and moisture protection, anti-tracking and tropicalisation on all types of electrical equipment. Supplied at a ready for use viscosity for dip and spray application.

SPECIFICATION

Viscosity	19 - 22 secs BS3900 PTA6 B4 flow cup at 25°C
Nonvolatile content	29 - 31%
Specific Gravity	0.91 - 0.94
Flash point	27°C
Shelf life	12 months at 21°C
Drying time	Touch dry 15 minutes Hard dry 45-60 minutes Full cure 24 hours

PROCESSING

Method	Dip or spray.
Viscosity	Dip Spray As supplied
Reducer	Ultimeg 2000 T4 thinner.

NOTE: Due to the introduction of improvements from time to time the right is reserved to supply products that may differ slightly from those illustrated or described in this publication.

Email: aev@aev.co.uk
www.aev.co.uk

AEV PLC,
Marion Street, Birkenhead,
Wirral. U.K CH41 6LT
Tel: ++ 44 (0) 151 647 3322
Fax: ++ 44 (0) 151 647 3377



ULTIMEG 2000-375

WORKSHOP PRACTICE

Procedure for dip impregnation of smaller components.

1. Ultimeg 2000-375 is supplied at a ready for use viscosity.
2. Immerse the components completely into the varnish for 1-10 minutes.
3. Drain components for 15-30 minutes over the varnish.
4. Cure

a) At ambient

45 minutes - 2 hours components can be handled, but only 50-70% of properties have developed and there is still residue solvent to be eliminated.

24-48 hours 95% of properties are developed and there are only trace quantities of solvent still present within components whereas in the majority of cases this trace of solvent is diffused slowly into the atmosphere causing no further problem, if the components are used or packed in materials such as polystyrene some attack can occur.

- b) The cure can be accelerated heating the components for 2 - 3 hours at 80°C will give an equivalent cure to 24 - 48 hours at ambient.

With heavily taped, tightly wound or larger components there is a risk of solvent entrapment. This risk is reduced by using a heat cure process.

The process each customer chooses depends on component size or design, film required, cure temperature and oven efficiency and thus only a guide can be given.

The cure times chosen is dependant on the size and type of component. Typical figures are given.

CURE TIMES

Time	15 mins	45-60 mins	24-48 hrs	2-3 hrs
Temperature (deg C)	21°C	21°C	21°C	80°C
Comment	Touch dry	Components handleable	Cured	Cured

PROPERTIES OF CURED VARNISH

Breakdown voltage	20°C	1200v/ml
Comparative tracking index		180
Flexibility		Pass 5mm (3/16") mandrell

HEALTH & SAFETY

Refer to Material Safety Data Sheet available.

PACKAGING

25 ltr, 5 ltr tins

AEV Plc Issue no. 1 Date: 11/97

NOTE: Due to the introduction of improvements from time to time the right is reserved to supply products that may differ slightly from those illustrated or described in this publication.

Email: aev@aev.co.uk
www.aev.co.uk

AEV PLC,
Marion Street, Birkenhead,
Wirral. U.K CH41 6LT
Tel: ++ 44 (0) 151 647 3322
Fax: ++ 44 (0) 151 647 3377